

https://repository.uaeh.edu.mx/revistas/index.php./MJMR/issue/archive

**Mexican Journal of Medical Research ICSa** 

Biannual Publication, Vol. 14, No. 27 (2026) 9-16



### Use of Bovine Teeth in Mexico as a Substitute for Human Dental Models Uso de Dientes Bovinos en México como Sustituto de Modelos Dentales Humanos

María Stella Pacheco Hernández<sup>a</sup>

#### Abstract:

Preclinical research and teaching in dentistry require dental models that simulate the characteristics of human teeth. However, ethical and logistical limitations associated with the use of human teeth have driven the search for viable alternatives. Bovine teeth have emerged as a suitable option due to their availability, lower cost, and structural and chemical similarities to human teeth. This article reviews the reasons for their selection, the specific characteristics of bovine breeds used in Mexico, the types of teeth employed, and their preparation. Size, content, and chemical composition data are presented with comparative tables.

#### Keywords:

Bovine teeth, dentistry, preclinical research, dental models, dental chemical composition, bovine breeds in Mexico.

#### Summary:

Preclinical research and teaching in dentistry require dental models that simulate the characteristics of human teeth. However, ethical and logistical constraints related to the use of human teeth have driven the search for viable alternatives. Bovine teeth have emerged as a suitable option due to their availability, reduced cost, structural and chemical similarities to human teeth. This article reviews the reasons for their selection, the specific characteristics of the cattle breeds used in Mexico, the types of teeth used and their preparation. Data on size, content and chemical composition are presented, as well as comparative tables.

#### Keywords:

Bovine teeth, dentistry, preclinical research, dental models, dental chemical composition, cattle breeds in Mexico.

#### INTRODUCTION

Dental models play an essential role in preclinical research and teaching. The use of human teeth presents ethical, legal, and logistical challenges, limiting their availability for experimental and educational studies. Bovine teeth have been frequently used in Mexico because of their structural similarities and availability in the livestock industry.<sup>1</sup>

In this context, bovine teeth have emerged as an alternative practice, because they have relevant structural and chemical similarities that make them an effective model for different applications,<sup>2</sup>

This article analyzes the classification of cattle breeds in Mexico, their suitability for the replacement of human teeth in dental studies, and the structural and chemical properties of bovine teeth. In addition, comparative tables are presented with data on size, composition and content of bovine teeth in relation to humans.

#### DENTAL MODELS IN DENTISTRY:

Modern dentistry relies on scientific research and evidencebased practice to improve treatments and oral health. In this context, dental models play a critical role in providing a means for the preclinical evaluation of techniques and materials prior to their application in human patients.<sup>3</sup> Models can be natural, such as human and bovine teeth, or artificial, such as resin replicas and digital simulators.

#### TYPES OF DENTAL MODELS AND THEIR APPLICATIONS

Dental models are classified into various categories according to their origin and purpose:

- **Natural models:** These include human and bovine teeth, widely used in adhesion, abrasion, erosion and biomaterial testing.<sup>4,5</sup>
- Artificial models: Made with synthetic resins or ceramics, they allow the standardization of comparative studies and the simulation of specific clinical conditions.<sup>6</sup>

<sup>a</sup> Corresponding author, Private Practice, https://orcid.org/0009-0005-2017-2269, Email: msph6193@gmail.com

Received: 21/02/2025, Accepted: 14/05/2025, Postprint: 23/05/2025, Published: 05/01/2026



• **Digital models:** Computerized dentistry has allowed the creation of virtual models that facilitate the planning of treatments and the simulation of occlusal forces.<sup>7</sup>

#### IMPORTANCE OF DENTAL MODELS IN RESEARCH AND TEACHING

The use of dental models has allowed significant advances in different areas of dentistry:

- **Biomaterial Evaluation:** Facilitate adhesion and strength testing of new restorative materials prior to clinical use.<sup>8</sup>
- **Training in restorative techniques:** They provide dental students with a tool to develop manual skills without risk to patients.<sup>9</sup>
- **Biomechanical analysis:** They allow the study of the distribution of forces in restorations, implants and dental prostheses.<sup>10</sup>

#### LIMITATIONS AND CONSIDERATIONS

Despite its many advantages, the use of dental models has certain limitations:

- Structural differences with human teeth: Artificial models may not accurately reproduce the microstructure of enamel and dentin, which can affect their mechanical and functional behavior. In addition, there are differences with human dental anatomy, such as crown morphology and dentin tubule arrangement, which may influence the validity of comparative studies.<sup>11</sup>
- Standardization of experimental conditions: It is essential to follow strict protocols in the collection, storage, and use of models to ensure the reproducibility of studies.<sup>12</sup>

## USE OF ANIMAL DENTAL MODELS IN DENTAL EXPERIMENTATION

Experimentation in dentistry requires models that allow treatments and biomaterials to be evaluated before their application in humans. Animal teeth have proven to be a viable alternative for in vitro and preclinical studies due to their anatomical and physicochemical characteristics comparable to those of human teeth.<sup>13</sup> In this context, the selection of the appropriate model depends on the structural similarity, availability, and ethical considerations associated with its use.<sup>13</sup>

#### MAIN ANIMAL DENTAL MODELS

Animal models used in dental experimentation include:

- **Bovine teeth:** They are widely used for their large size, availability, and structural similarity to human teeth, especially in dental adhesion and erosion studies.<sup>14</sup>
- **Porcine teeth:** They have a morphology and composition similar to human teeth, which makes

them suitable for research in periodontics and implantology.  $^{15}\,$ 

• Sheep and goat teeth: Used in studies of bone regeneration and biocompatibility of biomaterials due to the similarity of their alveolar bone to the human one.<sup>16</sup>

#### ETHICAL AND METHODOLOGICAL CONSIDERATIONS

The use of animal dental models in research should follow ethical principles that minimize suffering and promote the responsible use of these models. International regulations, such as those established by the International Committee on the Care and Use of Animals in Research, recommend the application of the principles of replacement, reduction and refinement to ensure ethical practices in experimentation, in accordance with the provisions of NOM-062-ZOO-1999.<sup>17</sup>

#### IMPORTANCE OF USING BOVINE TEETH

The use of bovine teeth as models in dental research has gained relevance due to their morphological and histological similarities with human teeth, as well as their accessibility and availability. This practice allows researchers and students to conduct in vitro studies and preclinical practices effectively and ethically.<sup>18</sup>

Bovine teeth have a histological composition and anatomical shape that make them ideal for use as substitutes for human teeth in research on dental materials.<sup>19</sup>

In addition, bovine tooth enamel has been used as an experimental model for dental research, providing updated information about the characteristics of bovine teeth in relation to their use as substitutes for human teeth in research work.<sup>20</sup>

However, it is important to recognize that there are differences between bovine and human teeth, such as variations. These differences must be considered when interpreting the results of the practices and when extrapolating conclusions to clinical practice.<sup>21</sup>

Although bovine teeth have some anatomical similarity to human teeth, they are not identical. There are significant differences, such as variations in the microhardness of the enamel, the arrangement and density of the dentin tubules, and the structural composition of the dentin. These differences should be considered when interpreting the results of experimental practices and when extrapolating conclusions to clinical practice, as they can influence the biomechanical response and the interaction with dental materials.<sup>22</sup>

#### JUSTIFICATION FOR THE USE OF BOVINE TEETH

Below is a classification of common breeds and their main attributes:

#### Table 1. Classification of cattle breeds.<sup>23</sup>

Race	Key features	Common Usage
Holstein	Uniform tooth size; Easy availability.	Adhesion and wear studies.
Brahman	High mechanical strength; thick enamel.	Testing of restorative materials.
Hereford	Homogeneous chemical composition; High durability.	Research in endodontic treatments.

These animals have teeth with structural characteristics similar to humans, which makes them ideal subjects for dental studies.<sup>24</sup>

#### **BOVINE DIET**

Cattle are ruminant herbivores and their diet is mainly composed of grass, hay, silage, and mineral and protein supplements. Diet influences tooth structure and wear, crucial aspects for research into dental materials.<sup>25</sup>

#### REASONS FOR CHOOSING CATTLE AS DENTAL MODELS

Cattle are chosen due to several advantages:

Adequate tooth size: Teeth, especially premolars and molars, have dimensions similar to those of humans.<sup>26</sup>

Availability: They are easy to obtain in slaughterhouses and farms.<sup>27</sup>

**Structure of enamel and dentin**: The mineral and mechanical composition of bovine teeth resembles that of humans.<sup>28</sup>

**Reduced cost**: Compared to primates or other models, cattle represent a more accessible and ethical alternative.<sup>29</sup>

#### CLASSIFICATION AND ADVANTAGES OF BOVINE TEETH

Bovine teeth are classified according to their anatomical function and their similarity to human teeth<sup>30</sup> the main types used are:

- Incisors: Due to their simple surface, they are ideal for dental aesthetics and adhesion studies. They offer a flat and uniform surface, facilitating the analysis of adhesive materials.<sup>31</sup>
- **Premolars:** Suitable for strength testing and restorative procedures. The larger size of the premolars and molars allows for more complex procedures to be performed and advanced clinical techniques to be compared.<sup>31</sup>
- **Molars:** Used mainly in biomechanical studies and endodontic treatments.<sup>31</sup>

#### DIMENSIONS OF BOVINE AND HUMAN TEETH

Table 2 shows a comparison of the average dimensions of bovine and human teeth, highlighting the key differences:

Table 2.	Comparative	table of bovine	and human	teeth. <sup>14</sup>
----------	-------------	-----------------	-----------	----------------------

Tooth Type	Length (mm)	Width (mm)	Enamel thickness (µm)		
Bovine incisor	15 - 20	6 - 8	300 - 400		
Human Incisor.	10 - 12	5 - 7	200 - 300		
Bovine molar	25 - 30	12 - 15	400 - 600		
Human molar	20 - 25	10 - 12	300 - 500		

## CHEMICAL COMPOSITION OF ENAMEL AND DENTIN

The chemical composition of bovine teeth is comparable to that of human teeth in terms of hydroxyapatite, collagen, water and mineral content as shown in Table 3.<sup>13</sup>

*Table 3.* Chemical composition of enamel and dentin of human and bovine teeth.<sup>13</sup>

	Enamel		Dentin	
Component	Huma n (%)	Bovine (%)	Human (%)	Bovine (%)
Hydroxyapatite	96	95	70	68
Collagen	0	0	20	22
Water	4	5	10	10
Minor minerals	<1	<1	<1	<1

Human tooth enamel coats the dentin in its crown portion like a cap, providing a protective barrier against the underlying dentin and pulp. It is the hardest tissue in the body, due to its high mineralization and the orderly arrangement of its prisms, which extend from the amelodentinal limit to the external surface, in contact with the oral environment. Its hardness lies in the absence of collagen and its chemical composition, characterized by 95% inorganic matrix and 0.36 - 2% organic matrix, composed mainly of proteins and polysaccharides.<sup>32</sup>

The inorganic component is made up of hydroxyapatite (HPA) crystals, composed of calcium phosphate and hydroxyl groups

(Ca10 [PO4] 6 [OH]<sub>2</sub>), with the possibility of incorporating ions such as magnesium, sodium, chlorine, potassium, carbonate and fluorine, which modify their physicochemical properties.<sup>33</sup> Despite its structural similarity to other mineralized tissues such as bone, dentin, and cementum, enamel is distinguished by the greater density and size of its HPA crystals.<sup>34</sup>

The structural unit of the enamel is the prism, which is made up of the compact arrangement of HPA crystals. However, its microscopic study is complex due to the optical interference generated by its crystalline composition and the variability in the orientation of the crystals within each prism. In addition, the enamel has secondary structural units, caused by variations in the degree of mineralization, the arrangement of the prisms, the enamel-dentin interaction and exposure to environmental factors.<sup>35</sup>

From a morphological point of view, HPA crystals adopt an elongated hexagonal shape when observed in cuts perpendicular to their longitudinal axis, while in parallel cuts they present a rectangular configuration.<sup>36</sup> These crystals are formed by the aggregation of unit cells, which constitute the structural basis of crystalline minerals.<sup>37</sup>

Water is the third component of enamel and is located on the periphery of the crystals, forming the so-called hydration layer. As you go deeper into the crystal, you find the layer of absorbed ions and compounds. The water content in the enamel progressively decreases with the age of the tooth, which influences its biomechanical properties.<sup>38</sup>

The process of enamel formation, known as amelogenesis, begins in the sixth week of intrauterine life. This phenomenon involves the synthesis of an organic matrix on which mineral salts are deposited.<sup>37</sup> Classically, dental embryogenesis is described in four successive stages: yolk, cap, bell and tooth follicle.<sup>38</sup> During this process, ameloblasts and intermediate stratum cells secrete the organic matrix of HPA enamel and crystals, resulting in their mineralization.<sup>39</sup>

Three essential proteins are involved in this phase: amelogenin (90%), which regulates the initiation and growth of crystals; enamel (5%), involved in the nucleation and extension of crystals; and ameloblastin (5%), which participates in the differentiation of ameloblasts. After completing the enamel formation, the ameloblasts disappear by apoptosis during tooth eruption, which gives the enamel its acellular and highly mineralized character.<sup>40</sup>

The hardness of enamel is due to its high HPA content, ranking fifth on the Mohs scale.<sup>41</sup> This gives it great resistance to abrasion and external forces, although its elasticity is low and depends on its water and organic matter content.<sup>42</sup> In the absence of dentin support, the enamel is prone to macroscopic and microscopic fractures. In addition, its translucency varies according to the degree of mineralization, which influences the perception of its color, which ranges from yellowish white to grayish white.<sup>43</sup>

Although enamel is highly impermeable, it can function as a semipermeable membrane, allowing the passage of water and

certain ions present in the oral environment. Its high mineralization also gives it a remarkable radiopacity, facilitating its study using imaging techniques.<sup>44</sup>

For dental research, the use of extracted human teeth requires institutional ethical approval. Given the difficulty of obtaining enough human teeth, teeth from different animal species have been used as an alternative.<sup>45</sup> It has been observed that the teeth of cattle, pigs, primates, sheep and horses have similar structural and physicochemical characteristics to human teeth, which allows their use in experimental studies.<sup>46</sup>

Research has shown that bovine incisors, in particular, have been successfully used in adhesion studies, microfiltration, trace element analysis, and morphological evaluation. Ortiz Ruiz et al.<sup>47</sup> compared the crystalline composition of enamel and dentin of various species, finding that human enamel has wider and lower crystals than those of other species, but with a greater structural similarity to bovine enamel.

For their part, Arango-Santander et al.<sup>46</sup> compared the microhardness of human and bovine enamel, finding similar values between the two, suggesting that bovine enamel could be a suitable experimental model for ex vivo studies in dental materials and shear resistance. However, it has been pointed out that the adhesion and tensile strength tests present some methodological heterogeneity, which requires a cautious interpretation of the results.<sup>48</sup>

Recent studies have shown that the dehydration of enamel influences its mechanical properties, increasing its hardness and reducing the coefficient of friction. These findings suggest that dehydrated enamel could exhibit superior mechanical behavior to hydrated enamel, which has implications for the research and application of dental biomaterials.<sup>49</sup>

#### PREPARATION OF BOVINE TEETH

#### • Collection and storage

Bovine teeth are mainly obtained from slaughterhouses, where they are collected under hygienic conditions. To prevent biological degradation, they are stored in disinfectant solutions such as sodium hypochlorite.<sup>50</sup>

#### • Sterilization

Microbiological safety is guaranteed by methods such as autoclaving or immersion in disinfectant solutions, preserving the tooth structure.<sup>51</sup>

#### Adaptation

The cutting and modeling of bovine teeth is done to replicate the dimensions of human teeth, optimizing their use in research and teaching.<sup>52</sup>

#### APPLICATIONS OF BOVINE TEETH IN DENTAL RESEARCH

Bovine teeth have been used in studies playing a crucial role in multiple areas of research:<sup>53</sup>

#### • Adhesion studies:

They allow the strength of bonding of restorative materials to the tooth structure to be evaluated.<sup>54</sup> Studies have shown that

bovine teeth can be used to evaluate the adhesion of composite resins, resin cements, and other restorative materials, providing results comparable to those obtained with human teeth.<sup>55</sup> Recent research has explored the influence of different surface preparation protocols on the adhesion of materials, analyzing techniques such as acid etching, the application of universal adhesives, and laser or plasma activation.<sup>56.57</sup>

Despite these advantages, it is important to consider the differences in microstructure and chemical composition between bovine and human teeth. For example, the lower density of bovine enamel and its prismatic characteristics can affect the infiltration of adhesive systems, which could influence the long-term bond strength.<sup>58</sup> However, when standardized protocols are implemented and comparative studies are conducted, bovine teeth remain a valuable tool for dental bonding research.

#### • Research on erosion and abrasion:

They facilitate the analysis of the effects of acids and abrasive agents on the enamel structure.<sup>59</sup> Dental erosion and abrasion are wear processes that compromise the structural integrity of teeth and affect their long-term functionality. To study these phenomena, experimental models play a key role in dental research.<sup>60</sup>

Dental erosion, mainly caused by exposure to extrinsic (food, drink) or intrinsic (gastric reflux) acids, has been investigated through the use of bovine teeth in in vitro studies. Research has evaluated the ability of different remineralizing agents, such as fluorides, hydroxyapatite nanoparticles, and biomaterials, in preventing acid wear.<sup>61,62</sup> Models based on bovine enamel have made it possible to analyze the mineral loss and effectiveness of protective strategies before their application in clinical studies.

On the other hand, dental abrasion, caused by mechanical factors such as excessive brushing or the use of abrasive toothpastes, has also been analysed using bovine teeth. Studies have compared the wear resistance of different restorative materials and enamels treated with protective agents.<sup>63</sup> Although bovine enamel has differences in microstructure and mineral density compared to human enamel, its controlled use under standardized experimental conditions allows extrapolable results to be obtained.<sup>64</sup>

We understand that bovine teeth are a fundamental tool in research on dental erosion and abrasion, facilitating the development and validation of preventive and therapeutic strategies. However, it is crucial to consider their limitations and complement the findings with studies in human teeth and clinical models to strengthen the validity of the results.

#### • Biomaterial Testing:

They are used to examine the durability and compatibility of composite resins, cements, and dental adhesives.<sup>65</sup> In biomaterial adhesion research, bovine teeth have served as a substrate for evaluating resin cements, dental adhesives, and protective coatings. Studies have shown that surface preparation protocols, such as acid etching and primer

application, influence the bond strength between biomaterials and bovine dental tissue, providing valuable information for the optimization of restorative materials.<sup>66,67</sup>

Likewise, bovine teeth have been used in mechanical resistance and wear tests of restorative materials. Research has evaluated the durability of composite resins, ceramics and hybrid materials subjected to simulated masticatory forces, which makes it possible to predict their behavior in the oral cavity.<sup>68</sup> In addition, in biocompatibility studies, these teeth have been used to analyze the response of mineralized tissue to new biomaterials with remineralizing or antibacterial properties.<sup>69</sup>

Despite its advantages, it is important to consider certain differences between bovine and human teeth, such as the higher porosity of bovine dentin and variations in enamel microstructure, which can influence the extrapolation of the results. However, when standardized methodologies are employed, bovine teeth continue to be an essential resource in the preclinical evaluation of dental biomaterials.

#### • Teeth whitening tests:

They are used to investigate the use of bleaching agents on the enamel structure.<sup>70</sup> Teeth whitening is a procedure widely used in cosmetic dentistry to remove pigmentation and improve the appearance of teeth. To evaluate the effectiveness and safety of bleaching agents, it is necessary to have experimental models that simulate the structure of human enamel.<sup>71</sup>

Bovine teeth have been used in in vitro studies to analyse the efficacy of different peroxides (hydrogen peroxide and carbamide peroxide), as well as the impact of factors such as the concentration of the whitening agent, the time of application and activation with light sources.<sup>72</sup> In addition, they have made it possible to evaluate changes in the structure of the enamel, measuring parameters such as microhardness, surface roughness and mineral loss after whitening treatments.<sup>73</sup>

Another relevant application of bovine teeth in teeth whitening trials is the comparison of strategies to reduce adverse effects, such as tooth sensitivity and demineralization. Research has explored the use of remineralizing agents, such as hydroxyapatite and fluoride, to counteract the erosive effects of bleaching products and preserve the structural integrity of enamel.<sup>74</sup>

Although bovine teeth have certain differences from human teeth, such as greater permeability of the enamel and a slightly different prismatic arrangement, their use in controlled experimental conditions allows valuable information to be obtained on the safety and efficacy of whitening treatments before their application in clinical practice.<sup>75</sup>

#### CONSIDERATIONS IN THE USE OF BOVINE TEETH

Despite their advantages, the use of bovine teeth in dental research requires certain precautions:

- Structural variability: Factors such as the age of the animal and its diet can influence the composition of the enamel and dentin.<sup>76</sup>
- **Differences in dentin permeability**: Although similar to human dentin, bovine dentin has greater

permeability, which can affect the interpretation of adhesion studies.<sup>77</sup>

• Need for standardization: It is essential to establish uniform protocols for the collection, storage and preparation of samples to ensure the reproducibility of the results.<sup>78</sup>



# Figure 1. Cattle breeds used in dental studies.<sup>79</sup> Mexico has several cattle breeds, including: Meat breeds (examples: Charolais, Brahman, Beefmaster) Dairy breeds (examples: Holstein, Jersey) Dual-purpose breeds (examples: Simmental, Swiss Brown)

Figure 1 shows the cattle breeds used in dentistry and selected according to specific characteristics such as size, structure and availability.<sup>79</sup>

#### PRECLINICAL TEACHING

In preclinical dental training in Mexico, the use of bovine teeth as models for practices and studies has gained relevance due to their similarities with human teeth and their easy access. This practice allows students to develop clinical skills in a controlled environment before caring for real patients.<sup>80</sup>

Bovine teeth share histological and morphological features with humans, making them viable substitutes for dental teaching and research, taking into account the difference in tooth size and structure. Its use in preclinical activities facilitates the understanding of procedures such as cavity preparation, the application of restorative materials and adhesion techniques. In addition, as they are more accessible and economical than human teeth, they represent a practical alternative for educational institutions.<sup>81</sup>

However, it is important to recognize that there are differences between bovine and human teeth, such as variations in the microhardness of the enamel and the structure of the dentin. One of the main differences is the **size**, as bovine teeth are significantly larger than humans, which can affect the distribution of forces and the adhesion of dental materials.<sup>14,30</sup> In addition, the morphology and arrangement of dental tissues also vary. For example, bovine dentin has a higher number of dentin tubules and a different orientation compared to human dentin, which can influence material leakage and structural strength. Also, the thickness of the enamel is different, which can alter the response to restorative and bonding procedures.<sup>13,30</sup> For these reasons, although bovine teeth are frequently used in dental research due to their availability and overall structural similarity, it is crucial to recognize and consider these differences in order to correctly interpret the results and their clinical applicability.<sup>82</sup>

In Mexico, although specific data on the prevalence of the use of bovine teeth in preclinical education are not available, several institutions have adopted this practice due to its pedagogical and logistical advantages. The implementation of bovine teeth in preclinical training contributes to the development of technical competencies in students, effectively preparing them for their future professional practice.<sup>83</sup>

The incorporation of bovine teeth in preclinical dental teaching in Mexico offers a valuable tool for the training of students, allowing the acquisition of practical skills in a safe and controlled environment.<sup>64</sup> However, it is essential that educators are aware of the limitations and differences between bovine and human teeth in order to ensure comprehensive and accurate training.<sup>84</sup>

#### CONCLUSION

The use of bovine teeth as models in dentistry represents, due to their chemical and structural similarities, an ethical, economic, and scientifically valid solution to human teeth, therefore, a viable alternative for research and teaching in dentistry in Mexico.

#### REFERENCES

- Yassen GH, Platt JA, Hara AT. Bovine teeth as substitute for human teeth in dental research: a review of literature. J. Oral Sci. 2011; 53(3): 273-82.
- [2] Goetz K, Gutermuth AC, Wenz HJ, Groß D, Hertrampf K. Ethical issues in dental education-A cross-sectional study with pre-clinical and clinical dental students. Eur. J. Dent. Educ. 2024; 28(3): 833-9.
- [3] Soares FZ, Follak A, da Rosa LS, Montagner AF, Lenzi TL, Rocha RO. Bovine tooth is a substitute for human tooth on bond strength studies: A systematic review and meta-analysis of in vitro studies. Dental Materials. 2016; 32(11): 1985-93.
- [4] Ferracane JL. Models of caries formation around dental composite restorations. J. Dent. Res. 2017; 96(4): 364–71.
- [5] Gelio MB, Zaniboni JF, Monteiro Jcc, Besegato JF, Pereira JR, Buchaim RL, et al. Medium-term evaluation of the bond strength and dentin penetration of self-adhesive resin cements to root dentin. Aust. Dent. J. 2024; 69(2): 93-101.
- [6] Anido-Anido A, Amore R, Lewgoy H, Anauate-Netto C, da Silva T, de Paiva Gonçalves S. (2012). Comparative study of the bond strength to human and bovine dentin in three different depths. Braz. Dent. Sci. 2012; 15(2): 56-62.
- [7] Ferreira Figueiredo de Carvalho M, Neiva Leijôto-Lannes AC, Nunes de Rodrigues MC, Capanema Nogueira L, Lyrio Ferraz NK, Nogueira Moreira A, et al. Viability of Bovine Teeth as a Substrate in Bond Strength Tests: A Systematic Review and Meta-analysis. J. Adhes. Dent. 2018; 20(6): 471-9.

- [8] Revilla-León M, Sadeghpour M, Özcan M. An update on applications of 3D printing technologies used for processing polymers used in implant dentistry. Odontology. 2020; 108(3): 331–8.
- [9] Baena Lopes M, Coelho Sinhoreti MA, Correr Sobrinho L, Consani S. Coparative study of the dental substrate used in shear bond strength tests. Pesqui. Odontol. Bras. 2003; 17(2): 171–5.
- [10] Perry S, Bridges SM, Burrow MF. A review of the use of simulation in dental education. Simul. Healthc. 2015; 10(1): 31–7.
- [11] Bakeman EM, Rego N, Chaiyabutr Y, Kois JC. Influence of ceramic thickness and ceramic materials on fracture resistance of posterior partial coverage restorations. Oper. Dent. 2015; 40(2): 211–7.
- [12] Reis AF, Giannini M, Kavaguchi A, Soares CJ, Line SRP. Comparison of microtensile bond strength to enamel and dentin of human, bovine and porcine teeth. J. Adhes. Dent. 2004; 6(2): 117-21.
- [13] Kajishima Konno AN, Coelho Sinhoreti MA, Consani S, Correr Sobrinho L, Xediek Consani RL. Storage effect on the shear bond strength of adhesive systems. Braz. Dent. J. 2003; 14(1): 42–47.
- [14] Attin T, Wegehaupt F, Gries D, Wiegand A. The potential of deciduous and permanent bovine enamel as substitute for deciduous and permanent human enamel: Erosion-abrasion experiments. J. Dent. 2007; 35(10):773–7.
- [15] Scherrer SS, Cesar PF, Swain MV. Direct comparison of the bond strength results of the different test methods: a critical literature review. Dent. Mater. 2010; 26(2): e78–93.
- [16] Goracci C, Sadek FT, Monticelli F, Cardoso PEC, Ferrari M. Influence of substrate, shape, and thickness on microtensile specimens' structural integrity and their measured bond strengths. Dent. Mater. 2004; 20(7): 643–54.
- [17] Oshiro Tanaka JL, Medici Filho E, Pereira Salgado JA, Castillo Salgado MA, de Moraes LC, de Moraes MEL, et al. Comparative analysis of human and bovine teeth: radiographic density. Braz. Oral. Res. 2008; 22(4): 346-51.
- [18] Khvostenko D, Hilton TJ, Ferracane JL, Mitchell JC, Kruzic JJ. Bioactive glass fillers reduce bacterial penetration into marginal gaps for composite restorations. Dent. Mater. 2016 Jan; 32(1): 73–81.
- [19] Alamdarloo Y, Mosaddad SA, Golfeshan F. Mechanical properties of combined packable and high-filled flowable composite used for the fixed retainer: an in vitro study. BMC. Oral. Health. 2024; 24(1):676.
- [20] Rüttermann S, Braun A, Janda R. Shear bond strength and fracture analysis of human vs. bovine teeth. PLoS. One. 2013; 8(3): e59181.
- [21 Franchini Pan Martinez L, Ferraz Nayara KL, Lannes Amanda CNL, , Rodrigues MC, De Carvalho MF, Zina LG, et al. Can bovine tooth replace human tooth in laboratory studies? A systematic review. J. Adhes. Sci. Technol. 2023; 37(7): 1279-98.
- [22] Ortiz-Ruiz AJ, Teruel-Fernández JD, Alcolea-Rubio LA, Hernández-Fernández A, Martínez-Beneyto Y, Gispert-Guirado F. Structural differences in enamel and dentin in human, bovine, porcine, and ovine teeth. Ann. Anat. 2018; 218: 7–17.
- [23] National Research Council. Guide for the Care and Use of Laboratory Animals. 8th ed. Washington, DC: National Academies Press; 2011.
- [24] Cochrane S, Burrow MF, Parashos P. Effect on the mechanical properties of human and bovine dentine of intracanal medicaments and irrigants. Aust. Dent. J. 2019; 64(1): 35-42.
- [25] Lee JJ, Nettey-Marbell A, Cook Jr A, Pimenta LAF, Leonard R, Ritter AV. Using extracted teeth for research: the effect of storage medium and sterilization on dentin bond strengths. J. Am. Dent. Assoc. 2007; 138(12): 1599-603.
- [26] Callejas Juárez N, Salas González JM. Estructura de la red de mercado de bovinos en México, 2017-2021. Rev. Mex. de cienc. pecuarias. 2023; 14(4): 745-59.

- [27] Krifka S, Börzsönyi A, Koch A, Hiller KA, Schmalz G, Friedl KH. Bond strength of adhesive systems to dentin and enamel—human vs. bovine primary teeth in vitro. Dent. Mater. 2008; 24(7):888–94.
- [28] Oesterle LJ, Shellhart WC, Belanger GK. The use of bovine enamel in bonding studies. Am. J. Orthod. Dentofacial Orthop. 1998; 114(5): 514– 9.
- [29] de Oliveira da Rosa WL, Piva E, Fernandes da Silva A. Bond strength of universal adhesives: a systematic review and meta-analysis. J. Dent. 2015; 43(7):765–76.
- [30] Bin AlShaibah WM, El-Shehaby FA, El-Dokky NA, Reda AR. Comparative study on the microbial adhesion to preveneered and stainless steel crowns. J. Indian Soc. Pedod. Prev. Dent. 2012; 30(3): 206–11.
- [31] Sahebi S, Sobhnamayan F, Hasani S, Mahmoodi N, Dadgar D. Bovine and Ovine Teeth as a Substitute for the Human Teeth: An Experimental Study. J. Dent. (Shiraz). 2024; 25(2): 132-7
- [32] Castellanos JE, Marín Gallón LM, Úsuga Vacca MV, Castiblanco Rubio GA, Martignon Biermann S. La remineralización del esmalte bajo el entendimiento actual de la caries dental. Univ. Odontol. 2013; 32(69): 49-59.
- [33] Bartlett JD, Simmer JP. New perspectives on amelotin and amelogenesis. J. Dent. Res. 2015; 94(5): 642-4.
- [34] Durso G, Tanevitch A, Abal A, Llompart G, Pérez P, Felipe P. Estudio de la micrestructura del esmalte dental humano en relación con la microdureza y la composición química. Rev. Cs. Morfol. 2017; 19(2): 1-9.
- [35] Teruel JD, Alcolea A, Hernández A, Ortiz Ruiz AJ. Comparison of chemical composition of enamel and dentine in human, bovine, porcine and ovine teeth. Arch. Oral Biol. 2015; 60(5): 768-75.
- [36] Cople Maia LC, Ribeiro de Souza IP, Aparecido Cury J. Effect of a combination of fluoride dentifrice and varnish on enamel surface rehardening and fluoride uptake in vitro. Eur. J. Oral. Sci. 2003; 111(1):68–72.
- [37] Yilmaz ED, Koldehoff J, Schneider GA. On the systematic documentation of the structural characteristics of bovine enamel: A critic to the protein sheath concept. Dent. Mat. 2018; 34(10): 1518-30.
- [38] Hurtado PM, Tobar-Tosse F, Osorio J, Orozco L, Moreno F. Amelogénesis imperfecta: Revisión de la literatura. Rev. Estomatol. 2015; 23(1): 32-41.
- [39] Hinostroza Izaguirre MC, Navarro Beteta RJ, Abal Perleche DM, Perona Miguel de Priego G. Factores genéticos asociados a la hipomineralización incisivo-molar. Revisión de literatura. Rev. Cient. Odontol. 2019; 7(1): 148–56.
- [40] Bronckers ALJJ. Ion transport by ameloblasts during amelogenesis. J. Dent. Res. 2017; 96(3): 243-53.
- [41] Ghadimi E, Eimar H, Marelli B, Nazhat SN, Asgharian M, Vali H, et al. Trace elements can influence the physical properties of tooth enamel. Springerplus. 2013; 2: 499.
- [42] Schmeling M. Selección de color y reproducción en odontología. Parte
   3: Escogencia del color de forma visual e intrumental. ODOVTOS-Int.
   J. Dental Sci. 2017; 19(1): 23-32.
- [43] Reyes-Gasga J. Estudio del esmalte dental humano por microscopía electrónica. Pädi Boletín Científico de Ciencias Básicas e Ingenierías del ICBI. 2021; 9(Especial2): 1–6.
- [44] Kiani AK, Pheby D, Henehan G, Brown R, Sieving P, Sykora P, Marks R, et al. Ethical considerations regarding animal experimentation. J. Prev. Med. Hyg. 2022; 63(2 Suppl 3): E255–66.
- [45] da Silva CL, Cavalheiro CP, Gimenez T, Imparato JCP, Bussadori SK, Lenzi TL. Bonding performance of universal and contemporary adhesives in primary teeth: a systematic review and network metaanalysis of in vitro studies. Pediatr. Dent. 2021; 43(3):170–7.

- [46] Arango-Santander S, Montoya C, Peláez-Vargas A, Ossa EA. Chemical, structural and mechanical characterization of bovine enamel. Arch. Oral Biol. 2020; 109: 104573.
- [47] Möhring S, Cieplik F, Hiller KA, Ebensberger H, Ferstl G, Hermens J, et al. Elemental compositions of enamel or dentin in human and bovine teeth differ from murine teeth. Materials. (Basel). 2023; 16(4):1514.
- [48] Atash R, Van den Abbeele A. Bond strengths of eight contemporary adhesives to enamel and to dentine: an in vitro study on bovine primary teeth. Int. J. Paediatr. Dent. 2005; 15(4): 264–73.
- [49] Hua LC, Wang WY, Swain MV, Zhu CL, Huang HB, Du ZR, et al. The dehydration effect on mechanical properties of tooth enamel. J. Mech. Behav. Biomed. Mater. 2019; 95: 210-4.
- [50] Hiraishi N, Gondo T, Shimada Y, Hill R, Hayashi F. Crystallographic and Physicochemical Analysis of Bovine and Human Teeth Using Xray Diffraction and Solid-State Nuclear Magnetic Resonance. J. Funct. Biomater. 2022; 13(4):254.
- [51] Moosavi H, Hajizadeh H, Mamaghani ZSZ, Rezaei F, Ahrari F. Comparison of various methods of restoring adhesion to recently bleached enamel. BMC Oral Health. 2024; 24(1): 942.
- [52] Lezcano MR, Enz N, Affur MC, Gili MA. Histological characteristics of bovine dentin using Masson's Trichrome staining. Rev. Cient. Odontol. (Lima). 2023; 11(4): e176.
- [53] Körner P, Gerber SC, Gantner C, Hamza B, Wegehaupt FJ, Attin T, et al. A laboratory pilot study on voids in flowable bulk-fill composite restorations in bovine Class-II and endodontic access cavities after sonic vibration. Sci. Rep. 2023; 13(1):18557.
- [54] Baia JCP, Oliveira RP, Ribeiro MES, Lima RR, Loretto SC, Silva E Souza MH. Influence of prolonged dental bleaching on the adhesive bond strength to enamel surfaces. Int. J. Dent. 2020; 2020(1): 2609359.
- [55] Koizumi H, Nakayama D, Komine F, Blatz MB, Matsumura H. Bonding of resin-based luting cements to zirconia with and without the use of ceramic priming agents. J. Adhes. Dent. 2012; 14(4): 385-92.
- [56] Frankenberger R, Reinelt C, Petschelt A, Krämer N. Operator vs. material influence on clinical outcome of bonded ceramic inlays. Dent. Mater. 2009; 25(8):960–8.
- [57] Borges GA, Sophr AM, de Goes MF, Correr Sobrinho L, Chan DCN. Effect of etching and airborne particle abrasion on the microstructure of different dental ceramics. J. Prosthet. Dent. 2003; 89(5): 479-88.
- [58] Reis AF, Giannini M, Lovadino JR, Ambrosano GM. Effects of various finishing systems on the surface roughness and staining susceptibility of packable composite resins. Dent. Mater. 2003; 19(1): 12–8.
- [59] Magalhães AC, Wiegand A, Rios D, Marques Honório H, Afonso Rabelo Buzalaf M. Insights into preventive measures for dental erosion. J. Appl. Oral Sci. 2009; 17(2): 75-86.
- [60] Lussi A, Carvalho TS. The future of fluorides and other protective agents in erosion prevention. Caries Res. 2015; 49 (Suppl 1):18-29.
- [61] Hove LH, Holme B, Young A, Tveit AB. The protective effect of TiF4, SnF2 and NaF against erosion-like lesions in situ. Caries Res. 2008; 42(1):68–72.
- [62] Ganss C, Schlueter N, Hardt M, von Hinckeldey J, Klimek J. Effects of toothbrushing on eroded dentine. Eur. J. Oral Sci. 2007; 115(5): 390– 6.
- [63] Amaechi BT, Higham SM. Dental erosion: possible approaches to prevention and control. J. Dent. 2005; 33(3): 243-52.
- [64] Borouziniat A, Majidinia S, Shirazi AS, Kahnemuee F. Comparison of bond strength of self-adhesive and self-etch or total-etch resin cement to zirconia: a systematic review and meta-analysis. J. Conserv. Dent. Endod. 2024;27(2):113–25.
- [65] Chatterjee N, Ghosh A. Current scenario on adhesion to zirconia; surface pretreatments and resin cements: A systematic review. J. Indian Prosthodont. Soc. 2022;22(1):13-20.

- [66] Vogl V, Hiller KA, Buchalla W, Federlin M, Schmalz G. Controlled, prospective, randomized, clinical split-mouth evaluation of partial ceramic crowns luted with a new, universal adhesive system/resin cement: results after 18 months. Clin. Oral. Investig. 2016; 20(9): 2481– 92.
- [67] Unsal KA, Karaman E. Effect of additional light curing on colour stability of composite resins. Int. Dent. J. 2022;72(3):346–52.
- [68] Devlukia S, Hammond L, Malik K. Is surface roughness of direct resin composite restorations material and polisher-dependent? A systematic review. J. Esthet. Restor. Dent. 2023; 35(6): 947–67.
- [69] Kwon SR, Wertz PW. Review of the Mechanism of Tooth Whitening. J. Esthet. Restor. Dent. 2015; 27(5): 240-57.
- [70] Joiner A. Whitening toothpastes: a review of the literature. J. Dent. 2010; 38(Suppl 2): e17-24.
- [71] Nunes Leite Lima DA, Faria e Silva AL, Baggio Aguiar FH, Liporoni PCS, Munin E, Bovi Ambrosano GM, et al. In vitro assessment of the effectiveness of whitening dentifrices for the removal of extrinsic tooth stains. Braz. Oral Res. 2008; 22(2): 106-11.
- [72] Torres CR, Wiegand A, Sener B, Attin T. Influence of chemical activation of a 35% hydrogen peroxide bleaching gel on its penetration and efficacy—an in vitro study. J. Dent. 2010; 38(10):838–46.
- [73] Bayne SC. Correlation of clinical performance with 'in vitro tests' of restorative dental materials that use polymer-based matrices. Dent. Mater. 2012; 28(1): 52-71.
- [74] Saleh F, Taymour N. Validity of using bovine teeth as a substitute for human counterparts in adhesive tests. East. Mediterr. Health J. 2003; 9(1-2): 201-7.
- [75] Dunn WJ, Söderholm KJ. Comparison of shear and flexural bond strength tests versus failure modes of dentin bonding systems. Am. J. Dent. 2001; 14(5):297-303.
- [76] DeWald JP. The use of extracted teeth for in vitro bonding studies: a review of infection control considerations. Dent. Mater. 1997; 13(2):74-81.
- [77] Richter C, Jost-Brinkmann PG. Shear bond strength of different adhesives tested in accordance with DIN 13990-1/-2 and using various methods of enamel conditioning. J. Orofac. Orthop. 2015; 76(2): 175– 87.
- [78] Osorio R, Pisani-Proenca J, Erhardt MC, Osorio E, Aguilera FS, Tay FR, et al. Resistance of ten contemporary adhesives to resin-dentine bond degradation. J. Dent. 2008; 36(2): 163–9.
- [79] Gomes de Oliveira S, Kotowski N, Rodrigues Sampaio-Filho H, Baggio Aguiar FH, Rivera Dávila AM, Jardim R. Metalloproteinases in Restorative Dentistry: An In Silico Study toward an Ideal Animal Model. Biomedicines. 2023; 11(11): 3042.
- [80] Lezcano MR. Dientes bovinos en odontología: Use of Bovine Teeth in Dentistry. Rev. Odontol. Científica Chilena. 2023; 2(1): 31-6.
- [81] Posada MC, Sánches CF, Gallego GJ, Peláez Vargas A, Restrepo LF, López JD. "Dientes de bovino como sustituto de dientes humanos para su uso en la odontología". Revisión de literatura. Rev. CES. Odontol. 2006; 19(1): 63-8.
- [82] Yavuz I, Tumen EC, Kaya CA, Dogan MS, Gunay A, Unal M, et al. The reliability of microleakage studies using dog and bovine primary teeth instead of human primary teeth. Eur. J. Paediatr. Dent. 2013; 14(1): 42–6.
- [83] Reeves GW, Fitchie JG, Hembree Jr JH, Puckett AD. Microleakage of new dentin bonding systems using human and bovine teeth. Oper. Dent. 1995; 20(6):230–5.
- [84] Jasinevicius TR, Landers M, Nelson S, Urbankova A. An evaluation of two dental simulation systems: virtual reality versus contemporary non-computer-assisted. J. Dent. Educ. 2004; 68(11): 1151-62.